



Date of issue : 05/01/2005

Last. mod. date : 11/05/2009

Product code**05331 RI-JET 75 PE GLOSS WHITE ASP 26 permanent WKPE 144****Description**

Gloss white polymeric soft vinyl allowing long term application even on slightly corrugated surfaces.

Solvent and eco-solvent ink-jet printing. The RI-JET series of ink jet print media give excellent print results with UV ink-jet printing. Testing for suitability between media, printers and inks is always recommended prior to use.

Solvent-based acrylic permanent adhesive.

For outdoor and indoor advertising and promotional applications.

Technical data**FACE MATERIAL**

| | |
|-------------------|----------------------|
| Type | Polymeric soft vinyl |
| Colour and Finish | White, gloss |
| Weight | 100g/m ² |
| Thickness | 75μ |

ADHESIVE

| | |
|-------------------|-------------------|
| Reference | RI - ASP26 |
| Type | Acrylic permanent |
| Min. Appl. Temp. | +10°C |
| Service Temp. | -20°C/ +120°C |
| Shear | Very high |
| Tack | Medium |
| Ultimate Adhesion | >15 |

RELEASE BACKING

| | |
|-------------------|---------------------|
| Type | 1 side clay coated |
| Colour and Finish | White |
| Weight | 144g/m ² |
| Thickness | 166μ |

CHEMICAL RESISTANCE

| | |
|----------------|--------------------|
| Detergent | No effect (24 Hrs) |
| Gasoline | No effect (1 Hrs) |
| SAE20 Motoroil | No effect (24 Hrs) |
| 10% HCl | No effect (10 min) |
| 10% NH4OH | No effect (10 min) |

Storage

The material must be stored at a temperature of 22°C +/- 2°C and 50% +/- 5% of Relative Humidity. Do not expose to direct sun light.

The area must be dry and clean. Please keep the material in the original packaging when not used in order to protect it from dust and contaminations.

All values presented in pdf data sheet are typical. Ritrama's data sheets provide only the general characteristics of the Product. It is the responsibility of the Customer and/or End User to determine that the Product is fit for the purpose for which the Customer and/or End User wish to use it. Ritrama can give no guarantee beyond the information given in the data sheet.